



# MONDO

## Specifications

Usage	Heavy Domestic
Composition	100% Polyester
Pattern Repeat	Plain
Width	140cm
Railroaded	Yes
Care Label	3U
Swish	Yes
Metres on roll (approx.)	45 metres
Price Code	Yellow
Fire Rated AS1530.3 Tested	Yes

## Test Results

Abrasion resistance - Martindale (ISO 12947)	28,000 cycles
Seam slippage (ISO 13936-2, Load 180)	Warp: 5.5mm, Weft: 5.0mm
Pilling resistance (ISO 12945-2)	4/5
Colourfastness to light (ISO 105-B02, blue std 6)	
Colourfastness to rubbing (ISO 105-X12:1993)	Dry: 4-5, Wet: 4-5
Free and hydrolysed formaldehyde (ISO 14184-1:1998)	Not detectable

Fabric may vary in colour due to the nature of the media

## Fire Rating AS1530.3 Results

Ignition Time	Standard Error: 0.36, Mean: 10.49 min
Flame Propagation Time	Standard Error: Nil, Mean: Nil sec
Heat Release Integral	Standard Error: 3.1, Mean: 39.7 kJ/m <sup>2</sup>
Smoke Release, log d	Standard Error: 0.0394, Mean: -0.8319
Optical Density, d	Mean: 0.1505 / Metre
Number of Specimens Tested and Ignited	6

### Regulatory Indices:

Ignitability Index	10 (Range 0-20)
Spread of Flame Index	0 (Range 0-10)
Heat Evolved Index	1 (Range 0-10)
Smoke Developed Index	5 (Range 0-10)